

11 -ELEVEN- **HC3D PLUS MULTILAYER BLOCK**
FOR BOTH ANTERIOR AND POSTERIOR RESTORATION

PHYSICAL PARAMETERS


- Color: vita 16 color+BL1/BL2/BL3/BL4
- Aesthetic: Ultra translucent
- Sintered Density.....6.0g/cm³
- Bending Strength.....700MPa to 1050MPa
- Light transmittance45% to 57%
- Sintering Temperature.....1500°C



FEATURES

- Suitable for anterior and posterior restoration
- Best translucency with strong strength
- 6 layers Multilayer color

RECOMMENDED INDICATIONS



AVAILABLE SHADES



12 -TWELVE- **HC4D PLUS MULTILAYER BLOCK**
FOR BOTH ANTERIOR AND POSTERIOR RESTORATION

PHYSICAL PARAMETERS


- Color: vita 16 color+BL1/BL2/BL3/BL4
- Aesthetic: Ultra translucent
- Sintered Density.....6.0g/cm³
- Bending Strength.....700MPa to 1200MPa
- Light transmittance43% to 55%
- Sintering Temperature.....1500°C



FEATURES

- Suitable for anterior and posterior restoration
- A multilayer color gradient, strength gradient, translucency gradient, fracture gradient
- High fracture toughness to resist chipping

RECOMMENDED INDICATIONS



AVAILABLE SHADES

